

Ruberoid® SBS Dual Smooth

Information Sheet

Updated: 12/08



*Quality You Can Trust Since 1886...
From North America's Largest Roofing Manufacturer™*



RUBEROID[®] SBS DUAL SMOOTH

Description

RUBEROID SBS DUAL SMOOTH membrane is a premium, heavy duty, modified bitumen membrane manufactured to stringent GAF Materials Corporation specifications. Its core is a strong, premium fiberglass/polyester/composite mat that is coated with an SBS polymer-modified asphalt and is smooth-surfaced. Smooth-surfaced mop applied installations must be protected with surfacing.

Uses

RUBEROID SBS DUAL SMOOTH is designed for new roofing and reroofing applications, as well as the construction of flashings. RUBEROID SBS DUAL SMOOTH is also an ideal product for repairs of built-up roofing membranes or other modified bitumen systems.

Advantages

- Guarantees are available for up to 20 years.
- No coating required for Class A ratings from UL.
- Cost effective—the installed cost of RUBEROID SBS DUAL SMOOTH is less than most premium fully-adhered systems on the market today.
- Lightweight—installed premium roof designs weigh less than 3 pounds per square foot.

Advantages (Continued)

- Resilient—RUBEROID SBS DUAL SMOOTH's heavy weight composite mat and core allow it to resist splits and tears due its strength, pliability and elongation characteristics.
- Durable—specially formulated modified asphalt gives RUBEROID SBS DUAL SMOOTH lasting performance.
- RUBEROID SBS DUAL SMOOTH is backed by GAF Materials Corporation, a company with over 100 years in the roofing business.



Applicable Standards

Meets ASTM D6162, Type II, Grade S

UL/ULc Listed

Products Specifications (nominal)

| | |
|---------------------|--|
| Roll Size | 1 square (109.8 gross sq.ft.) (10.2m ²) |
| Roll Length | 33.25' (10.1m) |
| Roll Width | 39.625" (1.0m) |
| Approx. Roll Weight | 95 lbs (43.1kg) |
| Product Thickness | 0.138" (3.5mm) |

This product meets or exceeds the following ASTM D6162, Type II, Grade S minimum requirements:

| Property | Test Method | Value |
|---------------------------------------|-------------|-------|
| Tensile Strength @ 0°F (min), lbf/in | ASTM D5147 | 125 |
| Elongation @ 0°F (min), % | ASTM D5147 | 2 |
| Low Temperature Flexibility (max), °F | ASTM D5147 | 0 |
| Tear Strength (min), lbf | ASTM D5147 | 90 |
| Dimensional Stability, (max) % | ASTM D5147 | 0.5 |