

TopCoat® One Step

Information Sheet

Updated: 1/04



*Quality You Can Trust Since 1886...
From North America's Largest Roofing Manufacturer™*



*“Don’t Repair Or Replace It...
Restore It And Save”*

ONESTEP

WATER-BASED, PRIMING TREATMENT



Designed For Use On:

- Metal



A liquid-applied corrosion inhibiting coating that is ideal for rusty/aged metal roofs not requiring a complete TOPCOAT® Roofing System.

TOPCOAT® ONESTEP:

- Chemical, salt, and corrosion protection for rusted metal roofs
- Cures and becomes stronger under the sun’s ultraviolet rays
- Non-flammable, low VOC and presents minimal hazard to the applicator or the environment
- Waterproof and self-priming for easy application in addition to superior protection
- Available in 5 and 55 gallon containers in addition to bulk totes
- Warranties available for up to 10 years*

TOPCOAT® ONESTEP:

TOPCOAT® ONESTEP can be applied to any metal roof that does not experience ponding water. Provides waterproofing and protection for many years.

*See warranties for complete coverage and restrictions.

**Quality You Can Trust Since 1886...from
North America’s Largest Roofing Manufacturer**



PRODUCT DATA

ONESTEP COATING

Water-based roof coating that does not require a primer for application over sound rusty metal. Unique UV resistant formula actually cures under the sun's ultraviolet rays. Chemical, salt and corrosion resistant; ideal for roofs not requiring a complete TOPCOAT® Roofing System. Do not apply over surfaces that experience ponding water or contain asphaltic materials, oils and fluropolymer finishes. Do not apply at temperatures below 42°F. Substrate temperatures must be below 120°F when applying this product.

Application Rate:	2 coats at 0.75 gallons/100 sq. ft. per coat
Application Method:	Airless sprayer
Application Temperature (air, surface):	42° - 120°F
Drying Time (75°F, 50% RH):	Tack-free in 2-3 hours
Wet Mil Thickness (0.75 gallon/100sq.ft.):	16 wet mils
Dry Mil Thickness (0.75 gallon/100sq.ft.):	6 dry mils
Total Solids (by weight):	49% +/- 2%
Total Solids (by volume):	40% +/- 2%
Specific Gravity:	1.23 +/- 0.1
Weight per Gallon:	10.2 +/- 0.5 lbs
Salt Spray Resistance:	ASTM 8117-300 hours (Pass)
Weatherability:	ASTM G-26-1500 hours (Pass) No cracking, blistering or adhesion loss
Viscosity (75°F):	5,000 +/- cps
Clean-up:	Water before curing
ASTM G-29, ASTM B-117, ASTM D-21-96, ASTM D-1475, ASTM E-1644	

NOTE: Repair leaks promptly to avoid adverse effects including mold growth.



Call for more information and a **FREE** brochure and video.

1-800-ROOF-411

www.gaf.com

