

# Brai® Supreme™ SBS Poly Smooth

## Data Sheet



*Quality You Can Trust Since 1886...  
From North America's Largest Roofing Manufacturer™*

# Brair<sup>®</sup> Supreme<sup>™</sup> - SBS Poly Smooth

## Technical Data Sheet

**PRODUCT:** Brair Supreme-SBS Poly Smooth, SBS Modified Bitumen Roof Membrane (formerly Intec<sup>®</sup> Flex S)

**DESCRIPTION:** Brair Supreme-SBS Poly Smooth is a durable, modified bitumen roof membrane designed and manufactured to meet the toughest industry and code requirements. Brair Supreme-SBS Poly Smooth is designed for use as a cap membrane, interply membrane or base sheet in modified bitumen and built-up roof systems. Brair Supreme-SBS Poly Smooth is manufactured with a strong, yet accommodating non-woven polyester mat which is saturated and coated with Styrene-Butadiene-Styrene (SBS) modified asphalt. **Note: When using Brair Supreme-SBS Poly Smooth as a cap membrane, it must be surfaced with asphalt and gravel.** Technical and sales information can be obtained through the U.S. Intec Technical Services Hotline, (800) 624-6832.

**APPLICATION:** Brair Supreme-SBS Poly Smooth can be applied with hot asphalt or cold adhesive.

**APPROVALS:** U.S. Intec products are listed or approved by the following agencies or code bodies: Underwriters Laboratories (UL), and cUL (Canada); Factory Mutual (FM); Int'l Council Bldg. Officials (ICBO); Southern Bldg. Code Congress Int'l (SBCCI); Miami Dade, FL. Contact U.S. Intec for applicable codes, government and insurance approvals.

**PRODUCT DATA:** Brair Supreme-SBS Poly Smooth (typical)

Weight . . . . . 88 lb/roll (40 kg/roll)  
 Roll Dimensions . . . . . 39 3/8" x 32'9" (1 m x 10 m)  
 Thickness . . . . . 3.8 mm (150 mils)  
 ASTM Designation . . . . . D6164, Type I, Grade S

PROPERTY (ASTM D 5147)	TEST METHOD	TEST RESULTS
Tensile Strength, 0°F, (MD/XD)	ASTM D 5147	100 lbf/in (17.5 kN/m)
Elongation (Max. load), 0°F, (MD/XD)	ASTM D 5147	70%
Tear Strength, (MD/XD)	ASTM D 5147	100 lbf (422 N)
Low Temperature Flexibility	ASTM D 5147	-5°F (-21°C)
Dimensional Stability	ASTM D 5147	<0.5%
Compound Stability	ASTM D 5147	220°F (104°C)

Data reported based on available independent and in-house resources. U.S. Intec reserves the right to change or modify, at its discretion, and without prior notice, any of the information, requirements, specifications or policies contained in this document.



1361 Alps Road  
 Wayne, NJ 07470  
 Technical Hotline (800) 624-6832  
 internet: [www.usintec.com](http://www.usintec.com) • email address: [support@usintec.com](mailto:support@usintec.com)