

TopCoat® Flashing Grade Spray

Information Sheet

Updated: 1/07



*Quality You Can Trust Since 1886...
From North America's Largest Roofing Manufacturer™*



FLASHING GRADE SPRAY FORMULA

Description

TOPCOAT® Flashing Grade Spray Formula is a light gray, water-based elastomeric sealant which is applied to seams, fasteners, flashings, and penetrations prior to the application of the TOPCOAT® Elastomeric Roofing Membrane. It is identical to regular TOPCOAT® Flashing Grade Formula with the exception of viscosity. It is designed to be easily applied with an airless sprayer. Like the TOPCOAT® Elastomeric Roofing Membrane, it has superior adhesion, flexibility and resistance to ultraviolet degradation.

Uses

Flashing Grade Spray Formula is designed for use on metal, wood, and concrete. Provides a seal along seams and around fasteners on metal roofs and excellent sealing around curbs and counter flashings. Do not apply at temperatures below 42°F. Substrate temperatures must be below 120°F when applying product.

Advantages

- A synthetic rubber sealant that cures in the ultraviolet rays of the sun
- Water-based; environmentally friendly and safe

- Strong; forms a flexible seal that will not become brittle
- Flexible; will expand and contract with metal roof
- Free from plasticizers and oils that will migrate out over time
- Required for joints, seams, penetrations, and fastener heads
- Applied with an airless sprayer (also available in brush or trowel grade)
- Warranties available for up to 10 years*
- Guarantees available for up to 20 years*
- Available in 1-gallon, 5-gallon and 55-gallon containers.

For application questions, please contact GAFMC Contractor Services at 1-800-766-3411.

Applicable Standards

ASTM D-412, ASTM D-21-96, ASTM D-1475, and ASTM E-1644

Note: Repair leaks promptly to avoid adverse effects, including mold growth.

**See warranties and guarantees for complete coverage and restrictions*

TOPCOAT® FLASHING GRADE SPRAY FORMULA TECHNICAL DATA

Application Rate (seams):	5 gallons/125 lineal ft. of seam (6" width)
Application Method:	Airless sprayer, brush or caulking gun
Application Temp (air, surface):	42° - 120°F
Drying Time (75°F, 50% RH):	Approximately 24 hours
Recommended Wet Mil Thickness:	105 wet mils
Recommended Dry Mil Thickness:	60 dry mils
Total Solids (by weight):	68% ± 1%
Total Solids (by volume):	56% ± 2%
Specific Gravity:	1.44 ± 0.1
Weight per Gallon:	12.0 ± 0.5 lbs
Viscosity (75°F):	140,000 ± 14,000 cps
Storage:	Store in well-ventilated area at 50°F to 80°F; protect from freezing
Shelf Life:	1 Year
Clean-up:	Water before curing



For further information, contact
GAF Contractor Services at:
1-800-766-3411 or visit www.gaf.com
©2007 GAF Materials Corporation 1/07