

TopCoat® XR-2000

Sell Sheet

Updated: 10/03



*Quality You Can Trust Since 1886...
From North America's Largest Roofing Manufacturer™*



*“Don’t Repair Or Replace It...
Restore It And Save”*

TOPCOAT® XR-2000

PRIMING TREATMENT



Designed For Use On:

- Metal

A liquid applied primer designed to enhance the adhesion of the TOPCOAT® Roofing System to pre-finished metal roofing, including those containing fluoropolymers such as Kynar® or siliconized polyesters.

TOPCOAT® XR-2000:

- Non-flammable, VOC compliant and easy clean up
- Good adhesion to factory coated metal roofing
- Has rust inhibiting properties
- Warranties available for up to 10 years*
- Available in 1-gallon, 5-gallon and 55-gallon containers

Recommended uses:

Enhance the adhesion of the TOPCOAT® Roofing System to pre-finished metal roofing, including those containing fluoropolymers such as Kynar® or siliconized polyesters.

*See warranties and guarantees for complete coverage and restrictions.



NO SEAMS. NO LEAKS. NO PROBLEMS.

**Quality You Can Trust Since 1886...from
North America’s Largest Roofing Manufacturer**



PRODUCT DATA

XR-2000

TOPCOAT® XR-2000 is a white, water-based adhesion promoting primer designed to enhance the adhesion of the TOPCOAT® Roofing System to pre-finished metal roofing, including those containing fluoropolymers such as Kynar® or siliconized polyesters. Due to the wide variety of pre-applied finishes, suitability of XR-2000 must be tested on an individual basis. Do not apply at temperatures below 42°F. Substrate temperatures must be below 120°F when applying product.

Application Rate:	0.75 gallon / 100 sq.ft.
Application Method:	Airless sprayer or roller
Application Temperature (air, surface):	42° - 120°F
Drying Time (75°F, 50% RH):	Approximately 6 hours
Recommended Wet Mil Thickness:	12 wet mils
Recommended Dry Mil Thickness:	5 dry mils
Total Solids (by weight):	52.5% + 1%
Total Solids (by volume):	40% ± 1%
Specific Gravity:	1.22 ± 0.1
Weight per Gallon:	10.2 ± 0.5 lbs
Viscosity (75°F):	3,500 ± 350 cps
Clean-up:	Water before curing

ASTM B-117, ASTM E-1644, ASTM C-794, ASTM D-1475

NOTE: Repair leaks promptly to avoid adverse effects including mold growth.



Call for more information and a **FREE** brochure and video.

1-800-ROOF-411
www.gaf.com



©2003 GAF Materials Corporation 10/03

