



QUICK SPEC

METAL – UNISIL HS

NOTE: The following “Quick Spec” is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

- Method**
- Spray, roller, or brush
- Requirements**
- Roof must be clean, dry, and tight.
 - Adhesion test required to ensure proper adhesion to substrate(s).
 - Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.
 - GAF recommends that the surface temperature be at or less than 105°F (40°C) during application.
- Application Instructions**
- Tighten and/or replace existing fasteners.
 - Power-wash roof to ensure it is free of dirt, debris, oil, and other contaminants that could negatively affect adhesion. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow roof to completely dry.
 - Install crickets to divert water and complete other necessary sheet metal repairs.
 - Prime rusty areas as needed.
 - Treat all metal seams.
 - Treat all roof penetrations, skylight curbs & rake edges.
 - Encapsulate fasteners with Unisil HS.
 - Apply coating per the chart below:

METAL - SEAMS UNISIL HS				
Warranty Term	Seam Type	Option (Choose one)	Total (Gal/Sq)	DFT* (mils)
10, 15 & 20 Year	Horizontal Seam**	3-course: Unisil HS and Fabric	3.00	52
		Unitape		25
	Vertical Seam	Unisil HS with Unisil Fiber		46

** DFT at horizontal seams includes 6 mils for the fabric.

METAL UNISIL HS						
Warranty Term	Coating		Total		Warranty	
	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Gal/Sq	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
10 Year	0.75	0.75	1.50	23	Yes	Yes
15 Year	1.00	1.00	2.00	31	Yes	Yes
20 Year	1.00	1.50	2.50	38	Yes	Yes

* DFT (Dry Film Thickness) is rounded to nearest mil and is theoretical. Actual DFT will vary dependent on substrate profile, application technique & waste factor.