

GAF Solar Reflective Products and Ratings for Cap Sheets, TPO and PVC - Updated 9-5-25 All Listed Products (click on the product name for product information and submittal documents) Thermal emittance and solar reflectance values shown on this table are values obtained for CRRC ratings. Other values for reflectance or emittance may vary based on test requirements. Title 24 is based on requirements effective January 1, 2020. Aged SRI (Title 24) is calculated using Aged Reflectivity and Initial Emissivity.											
Program Link	Initial Solar Reflectance	3 Yr. Solar Reflectance	Initial Thermal Emittance	3 Yr. Thermal Emittance	Initial SRI	Aged SRI	Aged SRI (Title 24)**	CRRC Product ID	Title 24	City of LA/LA County	LEED v4 Credit
CAP SHEETS											
Ruberoid® EnergyCap™ 30 Granule FR (Off-White)	0.73	0.60	0.90	0.90	90	72	72	0676-0017b	Not Eligible	Not Eligible	Contributes
GAFLAS® EnergyCap™ Mineral-Surfaced Cap Sheet (Off-White)	0.74	0.56	0.90	0.90	92	66	67	0676-0021b	Not Eligible	Not Eligible	Contributes
GAFLAS® EnergyCap™ Mineral-Surfaced Cap Sheet (Ultra Bright White)	0.73	0.67*	0.91	0.91*	91	82*	68	0676-0021c	Yes*	Not Eligible	Contributes
GAFLAS® EnergyCap™ Mineral-Surfaced Cap Sheet (Bright White)	0.71	0.67*	0.91	0.91*	87	82*	68	0676-0021d	Yes*	Not Eligible	Contributes
Ruberoid® EnergyCap™ Torch Granule FR (Off-White w/EnergyCote)	0.75	0.60	0.90	0.90	93	72	72	0676-0025b	Not Eligible	Not Eligible	Contributes
Ruberoid® EnergyCap™ Torch Granule FR (Ultra Bright White)	0.72	0.68*	0.92	0.91*	89	83*	67	0676-0025c	Yes*	Not Eligible	Contributes
Ruberoid® EnergyCap™ Torch Plus Granule FR (Ultra Bright White)											
Ruberoid® EnergyCap™ Torch Granule FR (Bright White)	0.71	0.68*	0.90	0.90	88	84*	67	0676-0025d	Yes*	Not Eligible	Contributes
Ruberoid® EnergyCap™ HW Plus Granule FR (Off-White)	0.73	0.60	0.90	0.90	90	72	72	0676-0026a	Not Eligible	Not Eligible	Contributes
Ruberoid® EnergyCap™ Mop Plus Granule FR (Off-White)	0.74	0.60	0.90	0.89	92	72	72	0676-0086a	Not Eligible	Not Eligible	Contributes
Ruberoid® EnergyCap™ Mop Plus Granule FR (Bright White)	0.72	0.63*	0.91	0.91*	88	77*	67	0676-0086b	Not Eligible	Not Eligible	Contributes
Ruberoid® EnergyCap™ HW Plus Granule FR (Bright White)											
Ruberoid® EnergyCap™ 30 Granule FR Asphaltic (Bright White)											
Ruberoid® UltraClad® SBS Membrane (Metallic)	0.87	0.70	0.05	0.12	94	60	57	0676-0161	Not Eligible	Not Eligible	Contributes
Ruberoid® EnergyCap™ Mop Plus Granule FR (Bright White)	0.74	0.53	0.91	0.91	92	62	63	0676-0163	Not Eligible	Not Eligible	Contributes
Ruberoid® EnergyCap™ HW Plus Granule FR (Bright White)											
Ruberoid® EnergyCap™ 30 Granule FR Asphaltic (Bright White)											
*CRRC Rapid Ratings (Interim laboratory-aged values that simulate weathered values which will be replaced with the measured three-year aged values upon completion of the weathering process.) **These are calculated values per Title 24 requirements and are not reflected on the CRRC website											

GAF Solar Reflective Products and Ratings for Cap Sheets, TPO and PVC - Updated 9-5-25 All Listed Products (click on the product name for product information and submittal documents) Thermal emittance and solar reflectance values shown on this table are values obtained for CRRC ratings. Other values for reflectance or emittance may vary based on test requirements. Title 24 is based on requirements effective January 1, 2020. Aged SRI (Title 24) is calculated using Aged Reflectivity and Initial Emissivity.											
Program Link	Initial Solar Reflectance	3 Yr. Solar Reflectance	Initial Thermal Emittance	3 Yr. Thermal Emittance	Initial SRI	Aged SRI	Aged SRI (Title 24)**	CRRC Product ID	Title 24	City of LA/LA County	LEED v4 Credit
SINGLE PLY MEMBRANES (TPO)											
EverGuard® TPO (White) and EverGuard® TPO Fleece-Back (White)	0.76	0.68	0.90	0.83	94	81	83	0676-0001	Yes	Yes	Contributes
EverGuard® TPO (Tan) and EverGuard® TPO Fleece-Back (Tan)	0.65	0.59	0.90	0.84	79	69	71	0676-0002	Not Eligible	Not Eligible	Contributes
EverGuard® TPO (Gray)	0.59	0.55	0.90	0.91	70	65	65	0676-0003a	Not Eligible	Not Eligible	Contributes
EverGuard® TPO FB Ultra and EverGuard® TPO Fleece-Back Membrane (White)	0.76	0.68	0.90	0.83	94	81	83	0676-0027	Yes	Yes	Contributes
EverGuard® TPO FB Ultra and EverGuard® TPO Fleece-Back Membrane (Tan)	0.65	0.59	0.90	0.84	79	69	71	0676-0028	Not Eligible	Not Eligible	Contributes
EverGuard® TPO FB Ultra and EverGuard® TPO Fleece-Back Membrane (Gray)	0.59	0.55	0.90	0.91	70	65	65	0676-0029	Not Eligible	Not Eligible	Contributes
EverGuard® TPO (Energy Tan) and EverGuard® TPO Fleece-Back (Energy Tan)	0.72	0.66	0.89	0.89	89	80	80	0676-0039	Yes	Yes	Contributes
EverGuard® TPO (Energy Gray) and EverGuard® TPO Fleece-Back (Energy Gray)	0.72	0.67	0.87	0.90	88	82	81	0676-0045	Yes	Yes	Contributes
EverGuard Extreme® TPO (White) and EverGuard Extreme® TPO Fleece-Back (White)	0.83	0.72	0.84	0.91	104	90	87	0676-0088	Yes	Yes	Contributes
EverGuard Extreme® TPO FB Ultra and EverGuard Extreme® TPO Fleece-Back Membrane (White)	0.83	0.72	0.84	0.91	104	90	87	0676-0094	Yes	Yes	Contributes
EverGuard Extreme® TPO (Energy Gray)	0.73	0.66	0.90	0.89	90	80	80	0676-0101	Yes	Yes	Contributes
EverGuard® SA TPO (White)	0.81	0.67	0.90	0.90	101	82	79	0676-0159	Yes	Yes	Contributes
SINGLE PLY MEMBRANES (PVC)											
EverGuard® PVC Smooth (White)	0.87	0.76	0.88	0.84	110	93	94	0676-0090	Yes	Yes	Contributes
EverGuard® PVC XK Fleeceback (White)	0.87	0.76	0.88	0.84	110	93	94	0676-0091	Yes	Yes	Contributes
EverGuard® PVC XK (White)	0.87	0.76	0.88	0.84	110	93	94	0676-0092	Yes	Yes	Contributes
EverGuard® PVC (White)	0.87	0.70	0.87	0.88	110	86	85	0676-0134a	Yes	Yes	Contributes
EverGuard® PVC Fleeceback (White)											
EverGuard® PVC KEE (White)	0.86	0.78	0.86	0.87	109	96	96	0676-0135a	Yes	Yes	Contributes
EverGuard® PVC KEE Fleeceback (White)											
EverGuard® PVC KEE (Energy Gray)	0.73	0.66	0.90	0.88	90	80	80	0676-0158	Yes	Yes	Contributes
EverGuard® PVC KEE Fleeceback (Energy Gray)											
*CRRC Rapid Ratings (Interim laboratory-aged values that simulate weathered values which will be replaced with the measured three-year aged values upon completion of the weathering process.) **These are calculated values per Title 24 requirements and are not reflected on the CRRC website											