



STREETBOND® DURASHIELD PAVEMENT COATING



QUICK SPEC

FLAT ASPHALT* – STREETBOND® DURASHIELD

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification.

Method

- Spray with a texture sprayer or can be applied by squeegee.

Requirements

- Apply when the ambient conditions are 50°F (10°C) and rising with no precipitation or freezing temperatures in forecast for 24 hours.
- Substrate temperature must be 50°F (10°C) and RISING.
- Keep traffic off coating until it is completely dry.

Application Instructions

1. Thoroughly clean the surface using a broom, backpack blower, or compressed air. Where dirt and debris is severe, power washing with United Cleaning Concentrate (UCC) or acceptable biodegradable cleaner may be required. UCC Cleaning Concentrate or acceptable biodegradable cleaner MUST be used where grease/oil stains are present. Care should be taken to ensure substrate is dry prior to applying the StreetBond® coating.
2. Mask off areas where coating or overspray is not wanted using plastic sheeting, tarps, coating shield, paper, or other suitable products.
3. In areas with polished asphalt, StreetBond® Adhesion Promoter must be used at a rate of one mixed unit per 500 ft² (46.5 m²).
4. Apply per the chart below. Subsequent coats can be applied as soon as the previous coat is dry enough to walk on.

DURASHIELD COATING COVERAGE AND RATE GUIDE (approx.)			
2 Coat Application	Flat Asphalt*		Limited Material Warranty
	Coat #1	Coat #2	3 year
Application Rate	1 gal/100 ft ² (4.1 L/m ²)	1 gal/100 ft ² (4.1 L/m ²)	

* Not recommended for use over stamped/imprinted asphalt.