



# DuraShield Pavement Coating

Technical Data Sheet



## PRODUCT DESCRIPTION

**StreetBond® DuraShield Pavement Coating** is a specialty coating, formulated using high-quality 100% acrylic polymer technology, designed to enhance the appearance of asphalt surfaces and to protect the asphalt from degradation due to oxidation from exposure to UV rays and water.

## PACKAGING & SHELF LIFE

3.75 gallons (14.2 liters) in a 5-gallon (18.9 liter) pail  
42 gallons (158.9 liters) in a 55-gallon (208 liter) drum\*  
\*One drum contains **12 units** (5-gallon [18.9 L] pails) of material.

Shelf Life: 18 months from date of manufacture in unopened containers, if stored properly in a clean and well-ventilated area at 40°F – 90°F (4°C – 32.2°C). Storage outside this temperature range may shorten shelf life. Keep containers covered when not in use. Do not allow material to freeze.

**GAF**  
1 Campus Drive  
Parsippany, NJ 07054  
1-800-ROOF-411  
gaf.com

*GAF Liquid-Applied*

December 2016, supercedes January 2016

For technical, system, and warranty information, visit [gaf.com](http://gaf.com) or call 1-800-766-3411.

## BASIC USES & ADVANTAGES

**StreetBond® DuraShield Pavement Coating** is used for the preservation & beautification of asphalt parking lots and asphalt walkways. The wear properties of **DuraShield Pavement Coating** are far superior to traditional asphalt emulsion seal coat products. The greatest improvement in wear occurs during wet exposures, where most coating loss typically occurs. **DuraShield Pavement Coating** covers minor surface cracks and imperfections.

### Advantages:

- **Superior Durability...** Engineered to last longer than typical asphalt coatings.
- **Simple and Easy Application...** Spray (textured sprayer), brush, roll, or squeegee the product onto the substrate.
- **Safer for the Environment...** Water-based formula with low odor that won't track onto adjacent surfaces like coal-tar or asphalt emulsion-based products.
- **Exceptional Flexibility...** Conforms to expansion and contraction of asphalt surfaces, preventing cracking and other accelerated asphalt damage

## PHYSICAL PROPERTIES

DURASHIELD PAVEMENT COATING	
Density	15.5 lb/gal, 1.85 g/mL [ASTM D1475]
Volume Solids	60% (±2) [ASTM D2697]
Weight Solids	77% (±2) [ASTM D2369]
VOC (calculated)	<25 g/L
Taber Abrasion (Dry - H-10 wheel)	0.78 g/100 cycles [ASTM D4060]
Taber Abrasion (Wet - H-10 wheel)	6.96 g/100 cycles [ASTM D4060]
Freeze Point	32°F (0°C)

Drying Time (Touch Dry)	1-4 hours at 77°F (25°C) and 40% humidity [ASTM D5895] *Required time will increase at higher humidity and/or lower temperatures.
Application Temperature (Air & Concrete)	+ 50°F - 105°F (Ambient) (10°C - 40°C)
Application Temperature (Pavement Surfaces)	+ 50°F - 140°F (Ambient) (10°C - 60°C)
Elongation	@ 70°F (21.1°C) >200 % (resin only)
Standard Colors	Asphalt, Solar Gray

## APPLICATION INSTRUCTIONS

**Substrate Preparation:** As a minimum, clean and prepare surfaces to receive coating by removing all loose and flaking particles, grease and laitance with the use of a stiff bristle push broom and or pressure washing. Care should be taken to ensure that the substrate is dry before applying the coating. In some cases additional drying time may be required after the cleaning process. If desired, **StreetBond® Adhesion Promoter Concentrate** can be used as part of the application process.

**Primer:** None needed if asphalt is in good condition without polished aggregates. Adhesion Promoter Concentrate should be used if the asphalt has polished aggregates present (occurs as asphalt ages and wear).

**Application:** **StreetBond® DuraShield Pavement Coating** should be applied in two coats at a minimum

total rate of 1 gallons/100 ft<sup>2</sup> (4.1 L/10 m<sup>2</sup>) depending on the asphalt texture, per coat by squeegee or sprayed using a texture sprayer and back-rolled. Apply in a smooth, generous coat to ensure **DuraShield Pavement Coating** fills minor surface cracks and imperfections.

Full cure-through occurs 6 – 24 hours after application and depends on temperature and humidity conditions. Coating must completely cure before opening up to traffic.

**For Application Questions:** Contact GAF Technical Services at 1-800-766-3411 or visit [gaf.com](http://gaf.com).

**Applicable Standards:** ASTM D1475, ASTM 2697, ASTM D2369, ASTM D4060, ASTM D5895

*continued on next page*



# DuraShield Pavement Coating

Technical Data Sheet

Page 2 of 2

## LIMITATIONS & PRECAUTIONS

Typical “seal coat” sprayers will not spray **StreetBond® DuraShield Pavement Coating** due to the special fibers used to minimize mud cracking. They will not allow **DuraShield Pavement Coating** to pass through the filter or spray nozzle. A texture sprayer must be used.

**DuraShield Pavement Coating** cannot be applied to freshly coated areas of “seal coat” products as it will not adhere properly.

No precipitation should be expected within 24 hours. Night-time installations are not recommended but if application must be done overnight, project areas require at least 6 hours of sunlight before opening the area to traffic.

Too high of a film build will cause cracking and/or not full cure-through. Do not open area up to traffic before **DuraShield Pavement Coating** fully cures.

## SAFETY & HANDLING

For specific information regarding safe handling of this material, please refer to the Safety Data Sheet (SDS).

## CLEAN-UP

Thoroughly rinse application equipment with clean water before it dries.

### GAF

1 Campus Drive  
Parsippany, NJ 07054  
1-800-ROOF-411  
gaf.com

*See applicable warranties and guarantees for complete coverage and restrictions.*