



QUICK SPEC

KYMAX™

METAL RESTORATION

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

Method

- Spray, roller, or brush apply Kymax™.

Requirements

- Roof must be clean, dry, and tight.
- Adhesion test required to ensure proper adhesion to substrate(s).
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.
- GAF recommends that the surface temperature be at or less than 105°F (40°C) during application.

Application Instructions

1. Tighten and/or replace existing fasteners.
2. Power-wash roof to ensure it is free of dirt, debris, oil, and other contaminants that could negatively affect adhesion. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow roof to completely dry.
3. Install crickets to divert water and complete other necessary sheet metal repairs.
4. Prime with Acrylex 400 Primer.
5. Before applying Kymax™, an adhesion test is required to ensure an adhesion of a minimum of 2.0 PLI. Test patches to be applied with rates listed below.
6. Apply per the chart below.

Kymax™ Metal Restoration					
Warranty Term	Acrylex 400 Primer	Kymax™			
	Total (Gal/Sq)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)
10 Year Extended Limited	0.50	0.40	0.40	0.80	4.50

* Actual DFT will vary dependent on substrate profile, application technique & waste factor.