



QUICK SPEC

ROOF MATE + KYMAX

ASPHALTIC

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

Method • Spray, roller, or brush

Requirements

- Moisture survey recommended.
- Roof must be clean, dry, and tight.
- Adhesion test required to ensure proper adhesion to substrate(s).
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.
- GAF recommends that the surface temperature be at or less than 105°F (40°C) during application.
- Do not apply over gravel surfaced asphaltic substrate.

Application Instructions

1. Conduct moisture survey and remove/replace all wet areas.
2. Repair membrane including seams, penetrations, flashings, curbs, and terminations with like materials.
3. Power-wash roof. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow roof to completely dry.
4. Prime using Roof Mate Base, Roof Mate MB Plus or UniBase.
5. Treat all roof penetrations, drains, curbs, and scuppers.
6. Treat all loose seams.
7. Treat "alligatored" areas or surface cracks.
8. Apply coating per the chart below:

ASPHALTIC ROOF MATE + KYMAX™													
Warranty Term	Roof Mate					Kymax™				System		Warranty	
	Product (Choose One)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	Total (Gal/Sq)	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
15 year [†]	Roof Mate & QS	1.50	1.50	3.00	26	0.40	0.40	0.80	4.5	3.80	30.5	Yes	No
	Roof Mate HT	1.50	1.50	3.00	25					3.80	29.5		
	Roof Mate MB Plus	1.50	1.50	3.00	26					3.80	30.5		

* Actual DFT will vary dependent on substrate profile, application technique & waste factor.

[†]Eligible for 10 year Extended Limited Warranty (color).