



QUICK SPEC

GRANULATED ASPHALTIC ROOF MATE™

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

- | | |
|---------------------------------|---|
| Method | <ul style="list-style-type: none"> Spray, roller, or brush |
| Requirements | <ul style="list-style-type: none"> Moisture survey recommended. Roof must be clean, dry, and tight. Adhesion test required to ensure proper adhesion to substrate(s). Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours. GAF recommends that the surface temperature be at or less than 110°F (43°C) during application. Do not apply over gravel surfaced asphaltic substrate. |
| Application Instructions | <ol style="list-style-type: none"> Before applying Roof Mate™, an adhesion test is required to ensure an adhesion minimum of 2.0 PLI. Test patches to be applied with rates listed below. Conduct moisture survey and remove/replace all wet areas. Repair membrane including seams, penetrations, flashings, curbs, and terminations with like materials. Power-wash roof. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow roof to completely dry. Prime using Roof Mate™ Base, Roof Mate™ MB Plus or UniBase. Treat all roof penetrations, drains, curbs, and scuppers. Treat all seams. Treat "alligatored" areas or surface cracks. Apply coating per the chart below: |

GRANULATED ASPHALTIC ROOF MATE™								
Warranty Term	Coating				Total		Warranty	
	Product (Choose one)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	3rd Coat (Gal/Sq)	Gal/Sq	DFT* (mils)	Emerald Pledge	Diamond Pledge
10 Year	Roof Mate™ & QS	1.50	1.50		3.00	25	Yes	No
	Roof Mate™ HT	1.50	1.50		3.00	25		
	Roof Mate™ MB Plus	1.50	1.50		3.00	26		
15 Year	Roof Mate™ & QS	1.50	1.50	1.50	4.50	38	Yes	No
	Roof Mate™ HT	1.50	1.50	1.50	4.50	38		
	Roof Mate™ MB Plus	1.50	1.50	1.00	4.00	35		

* DFT (Dry Film Thickness) is rounded to nearest mil and is theoretical. Actual DFT will vary dependent on substrate profile, application technique & waste factor.