



# QUICK SPEC

## CORRUGATED STRUCTURAL TRANSITE PANELS

### ROOF MATE™

**NOTE:** The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

- |                                 |  |
|---------------------------------|--|
| <b>Method</b>                   | <ul style="list-style-type: none"> <li>Spray, roller, or brush</li> </ul>  |
| <b>Requirements</b>             | <ul style="list-style-type: none"> <li>Moisture survey recommended.</li> <li>Roof must be clean, dry, and tight.</li> <li>Adhesion test required to ensure proper adhesion to substrate(s).</li> <li>Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.</li> <li>GAF recommends that the surface temperature be at or less than 110°F (43°C) during application.</li> </ul>   |
| <b>Application Instructions</b> | <ol style="list-style-type: none"> <li>Before applying Roof Mate™, an adhesion test is required to ensure an adhesion minimum of 2.0 PLI. Test patches to be applied with rates listed below.</li> <li>Repair or replace damaged or deteriorated sections with like materials, allowing cementitious products to cure properly.</li> <li>Power wash roof. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow the roof to completely dry.</li> <li>Prime with Epoxy Primer.</li> <li>Treat expansion joints with backer rod and compatible sealant. Control joints and transite gaps in excess of 1/16" (1.6mm) shall also be caulked.</li> <li>Treat all roof penetrations, drains, curbs, and scuppers.</li> <li>Treat all seams.</li> <li>Apply coating per the chart below:</li> </ol> |

CORRUGATED STRUCTURAL TRANSITE PANEL								
ROOF MATE™								
Warranty Term	Coating				Total		Warranty	
	Product (Choose one)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	3rd Coat (Gal/Sq)	Gal/Sq	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
10 Year	Roof Mate & QS	1.50	1.50		3.00	26	Yes	No
	Roof Mate HT	1.50	1.50		3.00	25		
	Roof Mate MB Plus	1.50	1.50		3.00	26		
	Roof Mate TCM	1.50	1.50		3.00	29		
15 Year	Roof Mate & QS	1.50	1.50	1.50	4.50	38	Yes	No
	Roof Mate HT	1.50	1.50	1.50	4.50	38		
	Roof Mate MB Plus	1.50	1.50	1.00	4.00	35		
	Roof Mate TCM	1.50	1.50	1.00	4.00	40		

\* DFT (Dry Film Thickness) is rounded to nearest mil. Actual DFT will vary dependent on substrate profile, application technique & waste factor.

**NOTE:** Corrugated Structural Transite Panels may contain asbestos. Follow all applicable local, state and federal regulations concerning asbestos. Under no circumstances does GAF have any liability for any damages, costs or expenses arising out of or associated with the pre-existing presence of asbestos-containing materials or any other allegedly hazardous substances or materials upon on the roof to which the new GAF roofing materials are being applied.