



QUICK SPEC

HYPALON®

UNISIL

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project.

- Method**
- Spray, roller, or brush
- Requirements**
- Moisture survey recommended.
 - Roof must be clean, dry, and tight.
 - Adhesion test required to ensure proper adhesion to substrate(s).
 - Apply at 40°F (5°C) °F and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.
 - GAF recommends that the surface temperature be at or less than 110°F (43°C) during application.
- Application Instructions**
- Before applying Unisil, an adhesion test is required to ensure an adhesion minimum of 2.0 PLI. Test patches to be applied with rates listed below.
 - Conduct moisture survey and remove/replace all wet areas.
 - Repair membrane including seams, penetrations, flashings, curbs, and terminations with like materials.
 - Power-wash roof. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow the roof to completely dry.
 - Treat all roof penetrations, drains, curbs, and scuppers.
 - Treat all seams.
 - Apply coating per the chart below:

HYPALON® UNISIL							
Warranty Term	Coating			Total		Warranty	
	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	3rd Coat (Gal/Sq)	Gal/Sq	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
10 Year	1.00	1.00		2.00	22	Yes	No
15 Year	1.50	1.25		2.75	30	Yes	No
20 Year	1.50	1.00	1.00	3.50	38	Yes	No

* DFT (Dry Film Thickness) is rounded to nearest mil and is theoretical. Actual DFT will vary dependent on substrate profile, application technique & waste factor.