



## GAF PMMA Primer

Adhesion Promoter

ITEM CODE: 9421



### Description:

GAF PMMA Primer Resin is a multi-component, fast-curing, PMMA resin primer for use over approved substrates and promotes Flashing Resin and Paste adhesion.

### Application:

Substrate Preparation — refer to the applicable GAF Installation Manual for detailed application information, including application coverage rates. Product must be catalyzed before application using GAF PMMA Catalyst Powder. See mixing charts that are supplied with GAF PMMA Catalyst products.

### Storage and Handling:

Store indoors in well-ventilated, cool, dry area away from heat, open fire, ignition sources, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Store jobsite materials on pallets in a shaded, well-ventilated area. Standard shelf life is 12 months; shelf life will be reduced when stored at temperatures above 77°F (25°C).

Refer to GAF PMMA Flashing System Guide for detailed mixing and application information.

See product packaging and the Safety Data Sheet (SDS) for specific information on the safe handling of this product.

### Packaging:

Resealable metal drums	10 kg (22 lb.)
Units Per Pallet:	48

### Specifications:

Colors	Translucent White
Conditions at Time of Application	Ambient & Substrate Temperatures: 32°F - 95°F (0°C - 35°C)
Typical Set/Cure Times at 68°F (20°C)	Rainproof: 25 Minutes Ready for Next Coat: 45 minutes
Pot Life at 68°F (20°C)	< 10 minutes
VOC Content	< 25 g/L (catalyzed) EPA Test Method 24

### GAF PMMA Primer Mixing Chart:

Paste Quantity	Ambient Temperature 77°F to 95°F (25°C to 35°C)			Ambient Temperature 41°F to 77°F (5°C to 25°C)			Ambient Temperature 32°F to 41°F (0°C to 5°C)		
	g	Tbsp.	0.1 kg Bags	g	Tbsp.	0.1 kg Bags	g	Tbsp.	0.1 kg Bags
1.0 kg (1 liter)	20	2	n/a	40	4	n/a	60	6	n/a
10 kg (10 liters)	200	n/a	2	400	n/a	4	600	n/a	6

Substrate temperature range for application of GAF PMMA Primer is 32°F to 95°F (0°C to 35°C).



Visit [gaf.com](http://gaf.com)

For additional information, contact GAF Design Services at 1-877-423-7663 or [designservices@gaf.com](mailto:designservices@gaf.com)

We protect what matters most™

