



Seam Tape – Data Sheet

PRODUCT DESCRIPTION

GAF Seam Tape consists of a coatable fabric surface backed with a polymer modified butyl adhesive. It is designed for application to a wide range of substrates where additional strength is required over loose or open seams and membrane tears.

Physical Properties¹

Tensile Strength	15 lb/in [ASTM D1000]
Elongation	100% [ASTM D1000]
Peel Strength	9 lbs. per lineal inch [ASTM D903]
Low Temperature Flexibility	Passes 180° bend over ½" mandrel at -30°F (-35°C) [Federal Test Method No. 141 a-6221]
Permeance	0.001 perms maximum
Tear Strength	150 pli (±25) [ASTM E96]
Service Temperature Limits	-20°F to 140°F (-29°C to 60°C)
Bond Time	Initial bond is immediate; full bond requires approximately 24 hours.

1. Values are approximate and subject to normal manufacturing variations. These values are not guaranteed and are provided solely as a guide.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION: Roof must have positive drainage, and be clean and dry with no trapped moisture. Priming of substrate is recommended and may be required. See *Liquid-Applied Roofing Manual* at gaf.com.

APPLICATION: Cut **GAF Seam Tape** to desired length with a knife or scissors. Slowly remove release paper backing and press firmly into place, centering the tape over the crack or seam. Avoid contamination of the adhesive before and during application. Remove any bubbles or buckling by pressing out by hand or utilizing a seam roller. Initial bond is immediate; full bond requires approximately 24 hours. Seam Tape must be coated over to prevent moisture contamination of the exposed fabric surface.

WARRANTY

Refer to applicable warranties and guarantees, available at gaf.com, for complete coverage and restrictions.

LIMITATIONS & PRECAUTIONS

APPLICATION SURFACE TEMPERATURE: 32°F – 110°F (0°C – 43°C).

Call GAF Design Services for temperature ranges outside these limits.

PACKAGING SIZES

50 ft. length rolls with the following widths: 4" and 6".

STORAGE & SHELF LIFE

Store rolls in a cool, dry area.

SHELF LIFE: 5 years in unopened containers, if stored properly.

SAFETY & HANDLING

For specific information regarding safe handling of this material, please refer to the Safety Data Sheet (SDS).

For application questions, contact GAF Design Services at **1-877-GAF-ROOF**

We protect what matters most™



2025 GAF 06/05 • COMCO309