



## Description:

RepairPro Trowel-Grade Sealant is a solvent-based synthetic, elastomeric high tensile, fiber reinforced, non-sagging vertical grade sealant that can be applied to many roof surfaces. It is durable and ideal for use on emergency repairs and maintenance applications and can be installed in challenging and even wet weather conditions.

## Approved Substrates:

RepairPro Trowel-Grade Sealant can be used on metal, structural concrete, copper, SBS, APP, EPDM, BUR, and TPO. It can also be used for repair applications on penetrations, curbs, and seams. Do not use over silicone substrates.

## Packaging Sizes:

- 10 oz. (296 mL) tube
- 1 gallon (3.8 liter) pail
- 3 gallon (11.4 liter) pail

## Storage and Shelf Life:

**Product Storage Temperature:** 40°F – 95°F (5°C – 35°C) Do not allow sealant to freeze.

**Shelf Life:** 24 months from date of manufacture in unopened containers, if stored properly in a clean and well-ventilated area.

## Warranty:

Refer to applicable warranties and guarantees, available at [gaf.com](http://gaf.com), for complete coverage and restrictions.



Visit [gaf.com](http://gaf.com)

For additional information, contact GAF Design Services at 1-877-423-7663 or [designservices@gaf.com](mailto:designservices@gaf.com)

## Application Instructions:

**Substrate Preparation:** All surfaces to be sealed must be clean and free from oil, grease, and any foreign matter. Excess water should be removed, if possible, before application. If necessary, and to provide a superior bond, any accumulated dirt should be removed by agitating with a stiff bristled nylon brush.

**Mixing:** Not required. Do NOT attempt to thin or self-tint.

**Application:** Apply with a roofer's trowel between 1/8" and 3/16" thick. Do not apply more than 1/4" thickness. Taper edges of the repair. When applying to wet surfaces, pressure is required to displace moisture and insure proper adhesion. Over-application on EPDM roofs may cause swelling of the EPDM.

## Limitations and Precautions:

**Application Air Temperature:** Min. 32°F (0°C). Do not heat containers.

**Application Surface Temperature:** 32°F (0°C) and rising. Care should be taken when coating surfaces above 120°F. Contact GAF Design Services if you have application questions.

## Safety and Handling:

For specific information regarding safe handling of this material, please refer to the Safety Data Sheet (SDS).

## Clean Up:

Mineral spirits or xylene.



We protect what matters most™

**Physical Properties — (ASTM D6694 / D6694M-21)**

Liquid Physical Property Requirements		
Type	ASTM Test Method	Test Values*
Volume Solids	ASTM D2697	59%
Weight Solids	ASTM D1644	62%
Film Physical Property Requirements		
Type	ASTM Test Method	Test Values*
Initial Percent Elongation	ASTM D2370	300%
Initial Tensile Strength	ASTM D2370	1700 psi (11,721 kPa)
Additional Physical Properties		
Type	ASTM Test Method	Test Values*
VOC	EPA 24	< 300.0 g/L
Weight per Gallon/Liters	ASTM D1147	9.24 lb. (1.10 kg)
Flash Point	—	103°F (39°C)
Standard Colors	—	White and Black (1 gallon)

**Approvals**

**State of Florida Approved**  
FL-620

\* Values are approximate and subject to normal manufacturing variations. These values are not guaranteed and are provided solely as a guide.