

GAF Sky-Lite Clear SEBS Coating



Description:

GAF Sky-Lite, is a clear, solvent-based synthetic rubber sealer designed to protect deteriorated fiberglass skylight panels and weathered plastic skylights.

Approved Substrates:

Fiberglass skylight panels and weathered plastic skylights.

Packaging Sizes:

- 5 gallon (19 liters) pail

Storage and Shelf Life:

Product Storage Temperature: 50°F – 90°F (10°C – 32°C) do not allow coating to freeze.

Shelf Life: 24 months from date of manufacture in unopened containers, if stored properly in a clean and well-ventilated area.

Application Instructions:

Substrate Preparation: : Surface must be clean and dry. See Liquid-Applied Roofing Manual at gaf.com.

Mixing: Mix uniformly for 3 minutes prior to use.

Application: Apply by brush, roller, or airless sprayer. Apply evenly at a rate of 1.0 gallons per 100 ft² (4.07 L per 10 m²) in a single coat with a minimum of two coats.

Warranty:

Refer to applicable warranties and guarantees, available at gaf.com, for complete coverage and restrictions.

Limitations and Precautions:

Application Air Temperature: min. 40°F (4°C). Do not heat containers.

Application Surface Temperature: 40°F (4°C) and rising. Care should be taken when coating surfaces above 120°F. Contact GAF Design Services if you have application questions. Do NOT apply if rain, dew, fog, heavy moisture, condensation, or freezing temperatures are in the 8-hour forecast to ensure proper cure. Cool temperatures/high humidity may slow curing.

Safety and Handling:

For specific information regarding safe handling of this material, please refer to the Safety Data Sheet (SDS).

Clean Up:

Use mineral spirits or xylene to thoroughly flush equipment.



Visit gaf.com

For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com

We protect what matters most™

GAF

Physical Properties

Type	ASTM Test Method	Test Values*
Volume Solids	ASTM D2697	37%
Weight Solids	ASTM D1644	39%
Weight per Gallon / per Liter	ASTM D1147	7.5 lb. (0.89 kg)
Tensile Strength	ASTM D 2370	1800 psi
Elongation	ASTM D 2370	1000%
VOC	—	< 550 g/L

* Values are approximate and subject to normal manufacturing variations. These values are not guaranteed and are provided solely as a guide