

GAF Surebond Primer



Description:

GAF SureBond Primer is a water-based acrylic primer used for sealing masonry and chalky surfaces.

Approved Substrates:

Masonry (brick, block, stucco, and concrete) and chalky coated surfaces.

Packaging Sizes:

- 2 gallon (7.6 liter) bucket
- 5 gallon (19 liter) pail

Storage and Shelf Life:

Product Storage Temperature: 50°F – 90°F (10°C – 32°C) do not allow coating to freeze.

Shelf Life: 18 months from date of manufacture in unopened containers, if stored properly in a clean and well-ventilated area.

Application Instructions:

Substrate Preparation: Clean and prepare surfaces by removing all loose and flaking particles, grease and laitance with the use of a stiff bristle push broom or power washing. Do not allow water to infiltrate the substrate during washing. Additional drying time may be required after the cleaning process. New concrete should be allowed to surface dry for at least 28 days before applying GAF SureBond Primer.

Mixing: Mix uniformly for a minimum of 3 minutes prior to use. Do NOT attempt to thin or self-tint.

Application: Apply GAF SureBond Primer by brush or roller at the rates specified below. Apply evenly at a rate of 0.25 – $0.5 \text{ gal./100 ft}^2$ (1.02 – 2.04 L/10 m^2) per coat.

Warranty:

Refer to applicable warranties and guarantees, available at gaf.com, for complete coverage and restrictions.

Limitations and Precautions:

Application Air Temperature: min. 50°F (10°C). Do not heat containers.

Application Surface Temperature: 50°F (10°C) and rising. Care should be taken when coating surfaces above 120°F. Contact GAF Design Services if you have application questions. Do NOT apply if rain, dew, fog, heavy moisture, condensation, or freezing temperatures are in the 8-hour forecast to ensure proper cure. Cool temperatures/high humidity may slow curing.

Safety and Handling:

For specific information regarding safe handling of this material, please refer to the Safety Data Sheet (SDS).

Clean Up:

Use water and soap to thoroughly flush equipment. If product has hardened, clean with solvent.



Visit gaf.com

For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com

We protect what matters most™



Physical Properties

Type	ASTM Test Method	Test Values*
Volume Solids	ASTM D2697	25%
Weight Solids	ASTM D 1644	23%
Density	—	8.5 lb./gal
VOC	—	<200 g/L

Approvals

	Miami-Dade County Product Control Approved 20-0130.07 and 21-0105.10	State of Florida Approved FL620 and FL20663
---	--	---

* Values are approximate and subject to normal manufacturing variations. These values are not guaranteed and are provided solely as a guide