

Brai® Supreme™ SBS Dual Granule FR

Data Sheet



*Quality You Can Trust Since 1886...
From North America's Largest Roofing Manufacturer™*

Brai® Supreme™ - SBS Dual Granule FR

Technical Data Sheet

PRODUCT: Brai Supreme - SBS Dual Granule FR, SBS Modified Bitumen Roof Membrane (formerly Intec® Flex Dual FR)

DESCRIPTION: Brai Supreme - SBS Dual Granule FR is a durable, fire-resistant modified bitumen roof membrane designed and manufactured to meet the toughest industry and code requirements. Brai Supreme - SBS Dual Granule FR is designed for use as a cap membrane in modified bitumen and built-up roof systems. Brai Supreme - SBS Dual Granule FR is manufactured with a premium, fiberglass/polyester composite reinforcement which is saturated and coated with Styrene-Butadiene-Styrene (SBS) modified asphalt and surfaced with mineral granules. Technical and sales information can be obtained through the U.S. Intec Technical Services Hotline, (800) 624-6832.

APPLICATION: Brai Supreme - SBS Dual Granule FR can be applied with hot asphalt or cold adhesive.

APPROVALS: U.S. Intec products are listed or approved by the following agencies or code bodies: Underwriters Laboratories (UL), and cUL (Canada); Factory Mutual (FM). Contact U.S. Intec for applicable codes, government and insurance approvals.

PRODUCT DATA: Brai Supreme - SBS Dual Granule FR (typical)

Weight 105 lb/roll (48 kg/roll)
 Roll Dimensions 39 3/8" x 32'9" (1 m x 10 m)
 Thickness 4.0 mm (160 mils)
 ASTM Designation D6162, Type II, Grade G

PROPERTY (ASTM D 5147)	TEST METHOD	TEST RESULTS
Tensile Strength, 0°F, (MD/XD)	ASTM D 5147	175 lbf/in (24.6 kN/m)
Elongation (Max. load), 0°F, (MD/XD)	ASTM D 5147	5%
Tear Strength, (MD/XD)	ASTM D 5147	145 lbf (645 N)
Low Temperature Flexibility	ASTM D 5147	-22°F (-30°C)
Dimensional Stability	ASTM D 5147	<0.5%
Compound Stability	ASTM D 5147	225°F (105°C)
Granule Embedment	ASTM D 5147	<2.0 g

Data reported based on available independent and in-house resources. U.S. Intec reserves the right to change or modify, at its discretion, and without prior notice, any of the information, requirements, specifications or policies contained in this document.



1361 Alps Road
 Wayne, NJ 07470
 Technical Hotline (800) 624-6832
 internet: www.usintec.com • email address: support@usintec.com