



ROOF MATE + KYMAX QUICK SPEC

SMOOTH & GRANULATED ASPHALTIC (KM-3)



NOTE: The following “Quick Spec” is an abbreviated specification and is not meant to replace the detailed specification. Read the entire 3-Part CSI System Specification prior to starting the project. Non-job specific 3-Part CSI System Specifications are available at www.gaf.com.

Method

Spray, roller, or brush

Requirements

- Moisture survey required.
- Roof must be clean, dry, and tight.
- Adhesion test required to ensure proper adhesion to substrate(s).
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 24 hours.
- GAF recommends that the surface temperature be at or less than 110°F (43°C) during application.
- GAF recommends that new asphaltic membranes and repairs age at least 30 days; 90+ days is ideal.
- Do not apply over gravel surfaced asphaltic substrate.

Application Instructions

1. Before applying Roof Mate and Kymax, an adhesion test is required to ensure an adhesion minimum of 2.0 pounds per linear inch (PLI). Test patches to be applied with rates listed below.
2. Conduct moisture survey and remove/replace all wet areas.
3. Repair membrane including seams, penetrations, flashings, curbs, and terminations with like materials.
4. Power wash roof to ensure it is free of dirt, debris, oil, and other contaminants that could negatively affect adhesion. United Cleaning Concentrate (UCC) is recommended to clean the roof. Allow roof to completely dry.
5. Prime using UniBase. When Roof Mate Base Coat or Roof Mate MB Plus are used, primer is not required.
6. Treat all roof penetrations, drains, curbs, and scuppers.
7. Treat “alligatored” areas or surface cracks.
8. All loose seams must be 3-coursed with flashing grade and fabric. All other seams must be treated with flashing grade only, no fabric required.
9. Apply coating per the chart below:

SEAMS & DETAILS ROOF MATE			
Treatment Type	Product	Total (Gal/Sq)	DFT* (mils)
3-Coursed Rates	Roof Mate Butter Grade and Fabric	4.0	43
Flashing Grade Only Rates	Roof Mate Butter Grade	2.0	19

SMOOTH & GRANULATED ASPHALTIC ROOF MATE + KYMAX													
Warranty Term	Roof Mate					Kymax				System		Warranty	
	Product (Choose one)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	Total Gal/Sq	DFT* (mils)	Emerald Pledge	Diamond Pledge
15 Year [†]	Roof Mate & QS	1.5	1.5	3.0	25	0.40	0.40	0.80	4.5	3.8	29.5	Yes	No
	Roof Mate HT	1.5	1.5	3.0	25					3.8	29.5		
	Roof Mate MB Plus	1.5	1.5	3.0	26					3.8	30.5		

* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor.

Note: DFT for 3-coursed rates includes 6 mils for the fabric.

[†]Eligible for 10 Year Extended Limited Warranty (color).