

MATRIX™ 202

SBS Flashing Cement

Updated: 8/16



*Quality You Can Trust...From
North America's Largest Roofing Manufacturer!™*



MATRIX™ 202

SBS FLASHING CEMENT (1 OF 2)

Highly Modified/
Smooth Application

Description

Matrix™ 202 SBS Flashing Cement is a high-quality, asbestos-free formulation for use as a cold-applied bonding agent for SBS modified bitumen roof systems. Heavy, "trowel-grade" consistency makes this product ideal for flashing details, attachment of membrane to steep slopes and parapet walls, and a variety of waterproofing repairs, especially at moving joints where its flexibility and elasticity make it superior to standard plastic cements.

- Superior bonding strength and high flexibility to accommodate temperature-related expansion and contraction of the roof system or waterproofing system
- Easy application...smooth, "trowel-grade" cement maintains excellent low-temperature flexibility

Uses

Matrix™ 202 SBS Flashing Cement's "trowel-grade" consistency outperforms standard plastic cements for:

- Attaching flashing to parapet walls, curbs, and roof projections
- Sealing end laps and perimeter edges of SBS modified bitumen membranes
- Sealing metal-edge flashing, gutter seams, air-conditioning ducts, etc.
- Repairing splits, breaks, and holes in roofing and flashing
- Sealing joints of metal roof panels, metal edging, gutters, coping caps, and air-conditioning ducts
- Flashing pipes and projections through below-grade damp-proofing membranes, sealing shingles, and repairing asphalt built-up, metal, and masonry roofs

Approvals & Certification

Matrix™ 202 SBS Flashing Cement is listed and approved by the following agencies or code bodies: Underwriters Laboratories (UL). Meets or exceeds the requirements of ASTM D4586 Asphalt Roof Cement Asbestos-free, Type I and ASTM D3409 Asphalt Roof Cement for Damp, Wet, or Underwater Surfaces. Approvals may vary by region. Be sure to review pail labels before purchase.



Surface Preparation

All surfaces must be clean, dry, and free from any foreign matter, such as oil, grease, dirt, or debris that could inhibit the bonding capabilities of the cement. On existing roofs, inspect roof deck condition; moisture in old roof may require complete removal of existing roof. Check local building codes; local building codes may require complete removal of existing roof. Contact GAF Technical Services for details on cutting out and repairing blisters, buckles, and raised edges for a smooth surface. Check all flashings, edges, drains, valleys, and vents, and repair as needed.

Application

Application Rate: Typical application rate is 8 gallons per square (3.26 L/m²) for a 1/8" (3 mm) coat.

Application Method: Use notched trowel or wide-edged putty knife to apply cement evenly and in equal amounts to substrate and SBS membrane flashing. Coat should be 1/8" (3 mm) thick on each surface, without gaps, dry areas, or bubbles.

Attachment: Membrane Flashing: No cure time before attaching flashing; simply press into place with even pressure, smoothing out wrinkles and bubbles. Adhere membrane to cemented substrate and press into place, working out any wrinkles or non-adhered areas and making sure a sufficient amount of cement is applied to the laps so that a bead of cement is visible at all lap edges. Mechanically fasten membrane flashing on parapet walls to avoid membrane slippage.

Coursing: Apply cement to surface and install glass or polyester fabric into cement; repeat method for desired courses. When finished, coat with another layer of cement.

Metal: All metal should be primed. Set metal flanges in full bead of 1/8" (3 mm) thick cement. Apply cement between joints and apply pressure so that a bead of cement is visible at joint edge.

Product Specifications (Nominal)

Weight	9.1 lb (4.1kg) per gallon
VOC (max)	300 grams/liter
Non-volatile content	50% maximum
SETA Flash Point	110°F (43.3°C)
Sizes	55 gallon/208.2 L

CODE APPROVALS



Cements and coatings for roofing systems as to external fire exposure.



MATRIX™ 202

SBS FLASHING CEMENT (2 OF 2)

Highly
Modified/
Smooth
Application

Application (Continued)

Sealing/Repairs: Apply cement at a 1/8" (3 mm) to 1/4" (6 mm) thickness, working the cement into the opening or crack and spreading beyond repair area approximately 2–4 inches (51–102 mm). If repair area is over 1/4" (6 mm) wide or more than 2" (51 mm) long, embed glass or polyester fabric into the cement for added reinforcement, then cover with additional cement. If desired, repeat procedure for coursing application and feather each layer of fabric beyond underlying layer.

Precautions

Compatibility & Limitations: Do not use with any APP modified products or any modified bitumen membranes that have a plastic film surface or are metal foil-faced. Do not use on wet or damp surfaces, directly over wood, or on surfaces previously covered with coal tar products. Do not install over or under polystyrene insulation.

Temperature Range: Apply only when temperatures are 45°F (7.2°C) and rising. Cold weather will cause product to stiffen, making application difficult. Store for 24 hours at room temperature prior to application. Do not heat container or attempt to thin this product. Not recommended for application on substrates that exceed 140°F (60°C).

Storage/Handling & FIRE WARNING: Matrix™ 202 SBS Flashing Cement is COMBUSTIBLE and should always be kept away from heat, open flame, and any source of ignition. Observe normal safeguards for storing and handling of this product prior to and during application. Do not allow flashing cement to freeze.

Important: Repair leaks promptly to avoid adverse effects, including, but not limited to, mold growth.

Clean Up

Keep containers covered when not in use. Clean equipment and overspray with kerosene, mineral spirits, or petroleum naphtha. Clean hands with waterless hand cleaner.

Caution

Matrix™ 202 SBS Flashing Cement contains petroleum distillate.

Ventilation – Use with adequate ventilation and close containers when not in use. If TLV (Threshold Limit Value) is exceeded, respirators are required (NIOSH/OSHA). Inhalation of high vapor concentration may result in headaches and/or dizziness. Remove individual to fresh air and administer oxygen if breathing is difficult. If breathing has stopped, administer artificial respiration, keep victim warm, and order emergency medical attention immediately.

Eye Contact – Rinse immediately with water for 15 minutes and seek medical advice.

Personal Protection – Irritation may result from prolonged or repeated contact with skin. Wear chemical-resistant gloves, protective goggles, and protective clothing, if needed.

Fire Protection – Matrix™ 202 SBS Flashing Cement is COMBUSTIBLE and should always be kept away from heat, open flame, and any source of ignition.

Waste Disposal – Empty containers must be disposed of in an approved landfill in accordance with local, state, and federal regulations.

For Application Questions

Contact GAF Technical Services at 1-800-766-3411 or visit gaf.com.