



RUBEROID®

30 GRANULE FR MEMBRANE

Formerly RUBEROID® 30 FR



Description

RUBEROID® 30 Granule FR Membrane is a fire-retarding modified bitumen membrane manufactured to stringent GAF specifications. Its core is a strong, resilient non-woven glass mat that is coated with an inherently fire-retardant SBS polymer modified asphalt and surfaced with mineral granules.

Uses

RUBEROID® 30 Granule FR Membrane is designed for new roofing, including GAF's 20/30 FR system and re-cover applications as well as in the construction of flashings. RUBEROID® 30 Granule FR Membrane is also an ideal product for repairs of built-up roofing membranes or modified bitumen systems.

Advantages

- System guarantees available for up to 15 years; select system constructions available with up to 20-year guarantee coverage.*
- Durable—RUBEROID® 30 Granule FR Membrane combines the strength of fiberglass reinforcement with the elongation characteristic of SBS modified asphalt.

Advantages (Continued)

- Light weight—Installed roof designs weigh less than 3 pounds per square foot (14.6 kg/m²).
- RUBEROID® 30 Granule FR Membrane is manufactured by GAF, a company with over 125 years in the roofing business.
- No coating required for Class A rating from UL.
- Available with black or white granules.

* See applicable guarantee for complete coverage and restrictions.

Applicable Standards

Meets ASTM D6163, Type I, Grade G
FM Approved
ICC ESR-1274
Miami-Dade County Product Control Approved
State of Florida Approved
Texas Department of Insurance
UL/ULC Classified

Product Specifications (nominal)

Roll Size	1 square (107.6 gross sq. ft.) (10.0 m ²)
Roll Length	32.8' (10.0 m)
Roll Width	39.375" (1.0 m)
Approx. Roll Weight	95.9 lb (43.50 kg)
Product Thickness	0.140" (3.56 mm)

This product meets or exceeds the following ASTM D6163, Type I, Grade G, minimum requirements:

Property	Test Method	Value
Tensile Strength @ 0°F (min), lbf/in	ASTM D5147	70
Elongation @ 0°F (min), %	ASTM D5147	1
Low Temperature Flexibility (max), °F	ASTM D5147	0
Tear Strength (min), lbf	ASTM D5147	35
Dimensional Stability, (max) %	ASTM D5147	0.5