



Acrylic Top Coat - Data Sheet

PRODUCT DESCRIPTION

GAF Acrylic Top Coat is a water based, acrylic elastomeric top coat that is part of the GAF Acrylic Coating System. **GAF Acrylic Top Coat** is designed to be applied over GAF Acrylic Base Coat. **GAF Acrylic Top Coat** forms a monolithic coating that helps provide protection against damage from the exposure to UV and weather elements. It is also effective in sealing and encapsulating spray polyurethane foam (SPF).

APPROVED SUBSTRATES

New and existing metal, structural concrete, TPO, PVC, Hypalon®, SPF, EPDM, and asphaltic roofs. New TPO and asphaltic roofs should be weathered for at least 30 days. Do NOT use on gravel-surfaced roofs or shingle roofs.

PACKAGING SIZES

5-gallon (18.9 liter) pail
55-gallon (208 liter) drum
275-gallon (1040 liter) tote

STORAGE & SHELF LIFE

PRODUCT STORAGE TEMPERATURE: 50°F – 90°F (10°C – 32°C) Do NOT allow coating to freeze.

SHELF LIFE: 18 months from date of manufacture in unopened containers, if stored properly in a clean and well-ventilated area.

APPLICATION

INSTRUCTIONS

SUBSTRATE PREPARATION: Roof must have positive drainage, and be clean and dry with no trapped moisture. Repair damaged membrane, flashings, and penetrations. Conduct test patches to verify adhesion of coating prior to start of work. Priming of substrate is recommended and may be required. See *Liquid-Applied Roofing Manual* at gaf.com.

MIXING: Mix uniformly for 3 minutes prior to use. Do NOT attempt to thin or self-tint.

APPLICATION: Apply by brush, roller, or airless sprayer evenly at the rates specified below. Do NOT apply more than 1.5 gallons per 100 ft² (6.1 L per 10 m²) in a single coat. Apply additional coats perpendicular to the previous coat once it is dry enough to walk on. Total coverage is dependent on the substrate. See below for minimum coverage requirements.

WARRANTY

Refer to applicable warranties and guarantees, available at gaf.com, for complete coverage and restrictions.

APPLICATION RATE FOR LIMITED WARRANTY ON GAF LIQUID-APPLIED ROOF COATINGS

Limited Warranty Term	5 Years	7 Years	10 years	12 years	15 years
Number of Gallons Per Square	2	2.5	3	3.5	4
Dry Film Thickness	17	21	25	29	34

For application rates and other requirements for system guarantees and warranties, see *Liquid-Applied Roofing Manual* at gaf.com.

LIMITATIONS & PRECAUTIONS

APPLICATION AIR TEMPERATURE: Min. 50°F (10°C). Do NOT heat containers.

APPLICATION SURFACE TEMPERATURE: 50 – 110°F (10°C – 43°C). Cool temperatures/high humidity may slow curing.

Do NOT apply if rain, dew, fog, heavy moisture, condensation, or freezing temperatures are in the 8-hour forecast to ensure proper cure.

Call GAF Technical Support Services for temperature ranges outside these limits.

SAFETY & HANDLING

For specific information regarding safe handling of this material please refer to the Safety Data Sheet (SDS).

CLEAN UP

Use water and soap to thoroughly flush equipment.

For application questions, contact GAF Technical Support Services at **1-877-GAF-ROOF**

We protect what matters most™



GAF Acrylic Top Coat – Data Sheet

PHYSICAL PROPERTIES (ASTM D 6083-21)

Table 1: Liquid Physical Property Requirements

Type	ASTM Test Method	ASTM Minimum Values	Test Values ¹
		Type I	
Volume Solids	ASTM D 2697	≥50%	53%
Weight Solids	ASTM D 1644	≥60%	66%

Table 2: Cured Film Physical Property Requirements

Type	ASTM Test Method	ASTM Minimum Values	Test Values ¹
		Type I	
Initial Percent Elongation	ASTM D 2370	Min. 100% @73°F	258%
Initial Tensile Strength	ASTM D 2370	Min. 200 psi @73°F	284 PSI
Final Percent Elongation	ASTM D 2370	Min. 100% @73°F	Pass
Permeance	ASTM D 1653	Max. 50 perms	Meets ASTM D6083
Accelerated Weathering	ASTM D 4798	No cracking/checking	1,000 hours: Pass
Low Temperature Flexibility	ASTM D 522	Min. Pass 0.5 in. mandrel -15°F	Passes Type 1

Table 3: Additional Physical Properties

Type	ASTM Test Method	Test Values ¹
Weight per Gallon/Liter	-	11.8 lb. (1.41 kg)
VOC	-	<25 g/L
Hardness	ASTM D2240	55-65 Shore A
Bond Strength	ASTM C 297	Exceeds cohesive strength of coating
Dry Time	ASTM D 5895	3 hours @ 70°F (21°C), 50% R.H. White @ 16 wet mils (406 microns) *Required time will increase at higher humidity and/or lower temperatures
High-Temperature Stability	ASTM D794	No age hardening up to 250°F (121°C)
Resistance to Wind-Driven Rain	Federal Specification TTC-555B	0.3% moisture result
Service Temperature Limits (Installed Coating)	-	-30°F to 200°F (-35°C to 93°C)
Standard Colors	-	White, Light Gray, Dove Gray, Gray, Cotton, Light Tan, Desert Sand , plus nine other colors. See GAF Roof Coatings Solution Guide. *Customized tinting available

1. Values are approximate and subject to normal manufacturing variations. These values are not guaranteed and are provided solely as a guide.

For specific physical property information on GAF Premium Acrylic HydroStop® Base Coat and Fabric components or information on GAF Premium Acrylic HydroStop® System, please refer to individual Technical Data Sheets.

APPROVALS

ANSI/UL 790 Class A	UL Listed*		
Factory Mutual (FM 4470)	FM Approved** Passes FM Severe Hail**		
State of Florida Approved (FBC)	FL620		
Miami-Dade County NOA	20-0130.07***		
Title 24	Rated by the Cool Roof Rating Council (CRRC) for use in Title 24 Projects		
CRRC (Cool Roof Rating Council) Coolroofs.org	WHITE - Smooth (Product ID 0614-0004a)		
	Solar Reflectance Initial: 0.83 Aged: 0.71	Thermal Emittance Initial: 0.92 Aged: 0.90	Solar Reflectance Index (SRI) Initial: 105 Aged: 87

*Refer to UL Product iQ for actual assemblies

**Refer to FM RoofNav for actual assemblies.

***Formerly known as Roofmate Top Coat



We protect what matters most™