

TOPCOAT® Liquid-Applied Roofing Systems

XR-2000

(TOPGN160)

Updated: 7/14



*Quality You Can Trust...From
North America's Largest Roofing Manufacturer!™*

XR-2000

Description

TOPCOAT[®] XR-2000 is a white, water-based, 100% acrylic adhesion-promoting primer designed to enhance the adhesion of the TOPCOAT[®] Roofing System to prefinished metal roofing. Due to the wide variety of preapplied finishes, suitability of XR-2000 must be tested on an individual basis.*

Uses

TOPCOAT[®] XR-2000 is designed to enhance the adhesion of the TOPCOAT[®] Roofing System to prefinished metal roofing, including those containing fluoropolymers such as Kynar[®] or siliconized polyesters. **For proper installation, substrate must have positive drainage (i.e., shall not pond water for a period longer than 48 hours).** Surface must be free of ponding water, ice, snow, and debris prior to application. Do not apply at temperatures below 42°F. Substrate temperatures must be below 120°F when applying product.

Advantages

- Non-flammable, VOC compliant, and easy clean-up
- Good adhesion to factory-coated metal roofing
- Has rust-inhibiting properties
- Limited material warranty available for up to 10 years**
- Available in 1-gallon, 5-gallon, and 55-gallon containers

For Application Questions

Contact GAF Technical Services at 1-800-766-3411 or visit gaf.com.

Applicable Standards

ASTM B117, ASTM E1644, ASTM C794, ASTM D1475

Note: Repair leaks promptly to avoid adverse effects, including mold growth.

*See TOPCOAT[®] metal specifications for testing procedure.

**See applicable warranties for complete coverage and restrictions.

TOPCOAT[®] XR-2000 TECHNICAL DATA

Application Rate:	0.75 gallon/100 sq. ft.
Application Method:	Airless sprayer or roller
Application Temperature (air, surface):	42° - 120°F
Drying Time (75°F, 50% RH):	Approximately 6 hours
Recommended Wet Mil Thickness:	12 wet mils
Recommended Dry Mil Thickness:	5 dry mils
Total Solids (by weight):	52.5% + 1%
Total Solids (by volume):	40% ± 1%
Specific Gravity:	1.22 ± 0.1
Weight per Gallon:	10.2 ± 0.5 lbs
Viscosity (75°F):	3,500 ± 350 cps
Storage:	Store in well-ventilated area at 50°F to 80°F; protect from freezing
Shelf Life:	1 year
Clean-Up:	Water before curing

LEED[®] Credit
Available



State of
Florida
Approved

