

Acrylic + KYMAX™ QUICK SPEC

SMOOTH & GRANULATED ASPHALTIC (KM-6)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at www.gaf.com.



METHOD REQUIREMENTS

Required:

- Moisture survey required
- Remove and replace any wet areas
- Repair membrane with like materials
- Roof must be clean, dry and tight
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 8 hours
- Adhesion test required
- Power washing required
- New membranes must be aged 30 days; 90 days ideal.

Recommendations:

- Refer to Technical Data Sheet for product specific application and surface temperature restrictions.

Restrictions:

Do not apply over gravel-surfaced substrates.

Installation Overview:

1. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0 pounds per linear inch (PLI). Test patches should be applied with rates listed below.
2. Power-wash substrate to remove contaminants that could negatively affect adhesion. Allow roof to completely dry.
3. Prime per chart below.
4. Treat "alligatored" areas, surface cracks, roof penetrations, drains, curbs and scuppers. (Refer to Substrate Preparation section for requirements)
5. All loose seams must be 3-coursed. All other seams must be treated with flashing grade only, no fabric required. (Refer to Seam Treatment Guide for requirements)
6. Apply coating per the chart below:

Surface Prep

	Product	Rate (Gal/Sq)
Cleaner	Cleaning Concentrate (diluted)	0.5 - 0.7
Primer*	Multi-Purpose Primer	0.5 - 1.0

*When Acrylic Base Coat or Bleed Block Base Coat are used, primer is not required.

SEAMS & DETAILS

Treatment Type	Product	Total (Gal/Sq)	Total (linear ft/gal)*	DFT* (mils)
3-Coursed Rates	Premium Brush-Grade Acrylic Flashing and Fabric	4.0	30	43
Flashing Grade Only Rates	Premium Brush-Grade Acrylic Flashing	2.0	100	19

Note: For other product options, please refer to our Seam Treatment Guide.

*Flashing rates are based on a 6" (152 mm) width.

SMOOTH & GRANULATED ASPHALTIC

Coverage Term	ACRYLIC					Kymax™				Total		Warranties/Guarantees Available+	
	Product (Choose one)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	Total Gal/Sq	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
15 Year	Premium Acrylic HydroStop® Top Coat	1.50	1.50	3.00	25	.40	.40	.80	4.50	3.80	30	Yes	No
	High Tensile Acrylic Top Coat	1.50	1.50	3.00	25	.40	.40	.80	4.50	3.80	30	Yes	No
	Acrylic Top Coat	1.50	1.50	3.00	26	.40	.40	.80	4.50	3.80	31	Yes	No
	WOB Acrylic TopCoat®	1.50	1.50	3.00	28	.40	.40	.80	4.50	3.30	33	Yes	No

* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor. Note: DFT for 3-coursed rates includes 6 mils for the fabric.

+ Eligible for Kymax TM Roofing Coating 10-Year Limited Warranty (color) in addition to the enhanced system warranty or guarantee.