

## GRO DECKING & DIMENSIONAL LUMBER

GRO South American decking and dimensional hardwood comes in most common sizes for traditional deck building. These hardwoods are exceptionally durable, hard, stable across a broad temperature and humidity range, and resistant to twisting and warping. Ideal for roof deck patios, railings, and walkways that are often exposed to extreme temperature and weather conditions.



MATERIAL	Ipe / Tabebuia sp. Garapa / Apuleia leiocarpa					
DIMENSIONS - IPE	Nominal	Actual	Nominal	Actual	Nominal	Actual
	2" x 4"	1½" x 3½"	1" x 4"	¾" x 3 ½"	5/4" x 4"	1" x 3 ½"
	2" x 6"	1½" x 5 ½"	1" x 6"	¾" x 5 ½"	5/4" x 6"	1" x 5 ½"
	2" x 8"	1½" x 7 ¼"	1" x 8"	¾" x 7 ¼"	5/4" x 8"	1" x 7 ¼"
	2" x 10"	1½" x 9 ¼"	1" x 10"	¾" x 9 ¼"	5/4" x 10"	1" x 9 ¼"
DIMENSIONS - GARAPA	Nominal	Actual	Nominal	Actual	Nominal	Actual
	2" x 4"	1½" x 3½"	1" x 4"	¾" x 3 ½"	5/4" x 4"	1" x 3 ½"
	2" x 6"	1½" x 5 ½"	1" x 6"	¾" x 5 ½"	5/4" x 6"	1" x 5 ½"
	2" x 8"	1½" x 7 ¼"				
COLOR / GRAIN	<p>Ipe: Typically reddish brown color, but can vary from olive brown to blackish, with lighter or darker striping / Fine to medium grain always interlocked</p> <p>Garapa: Warm pale yellow to honey brown / Mixed fine to slightly coarse grain</p>					
DURABILITY / RATING	<p>Ipe: Class A</p> <p>Garapa: Class B</p>					
HARDNESS (JANKA)	<p>Ipe: 3680</p> <p>Garapa: 1630</p>					
CHARACTERISTICS	<p>Resists termites, decay, and mold</p> <p>Wear and scuff resistant</p> <p>Weathers without splintering</p> <p>Low maintenance</p> <p>Resists bending, shearing, warping, and twisting</p>					

