

KYMAX™ QUICK SPEC

METAL RESTORATION (KM-9)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at www.gaf.com.



METHOD REQUIREMENTS

Required:

- Roof must be clean, dry and tight
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 8 hours
- Adhesion test required
- Power washing required

Recommendations:

- Refer to Technical Data Sheet for product specific application and surface temperature restrictions.

2. Tighten/replace existing fasteners. Encapsulate with appropriate flashing material.
3. Power-wash substrate to remove contaminants that could negatively affect adhesion. Allow roof to completely dry.
4. Install crickets to divert water and complete other necessary sheet metal repairs.
5. Prime per chart below.
6. Apply coating per the chart below:

Installation Overview:

1. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0 pounds per linear inch (PLI). Test patches should be applied with rates listed below.

CLEAN / PRIME			SEAMS & DETAILS				
	Product	Rate (Gal/Sq)	Treatment Type	Product	Total (Gal/Sq)	Total (linear ft/gal)*	DFT* (mils)
Cleaner	Cleaning Concentrate (diluted)	0.5 - 0.7	3-Coursed Rates	Premium Brush-Grade Acrylic Flashing and Fabric	4.0	30	43
Primer	Metal Roof Primer	0.3 - 0.5	Flashing Grade Only Rates	Premium Brush-Grade Acrylic Flashing	2.0	100	19

Note: For other product options, please refer to our Seam Treatment Guide.

*Flashing rates are based on a 6" (152 mm) width.

METAL RESTORATION KYMAX™					
Warranty/ Guarantee term	Metal Roof Primer	Kymax™			
	Total (Gal/Sq)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)
10 Year Limited (color)	0.50	0.50	0.50	1.00	5

* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor.