

PREMIUM ACRYLIC HYDROSTOP® FABRIC REINFORCED + KYMAX QUICK SPEC SMOOTH ASPHALTIC (LAR-35)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at www.gaf.com.



METHOD REQUIREMENTS

Required:

- Moisture survey required.
- Remove and replace any wet areas.
- Repair membrane with like materials.
- Roof must be clean, dry, and tight.
- Adhesion test required.
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in the forecast for 8 hours.
- New asphaltic membranes and should be aged at least 30 days; 90+ days is ideal.

Restrictions:

Do not apply over gravel surfaced asphaltic substrate.

Recommendations:

- Refer to Technical Data Sheet for product specific application and surface temperature restrictions.

Installation Overview:

1. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0 PLI. Test patches to be applied with system rates listed below.
2. Power wash substrate to remove contaminants that could negatively affect adhesion.
3. Prime per chart below.
4. Treat "alligatored" areas or surface cracks, roof penetrations, drains, curbs and scuppers.
5. Apply coating per the chart below.

CLEAN/ PRIME		
	Product	Rate (Gal/Sq)
Cleaner	Cleaning Concentrate (diluted)	0.5 - 0.7
Primer	Multi-Purpose Primer	.67-1.0

SEAMS & DETAILS				
Treatment Type	Product	Total (Gal/Sq)	Total (linear ft/gal)*	DFT* (mils)
3-Coursed Rates	Premium Brush-Grade Acrylic Flashing and Fabric	4.0	30	43
Flashing Grade Only Rates	Premium Brush-Grade Acrylic Flashing	2.0	100	19

Note: For other product options, please refer to our Seam Treatment Guide.
*Flashing rates are based on a 6" (152 mm) width.

SMOOTH ASPHALTIC														
	Premium Acrylic HydroStop Base Coat (with fabric)		Premium Acrylic HydroStop® Top Coat				Kymax				System		Warranties/ Guarantees Available*	
	Total (Gal/Sq)	DFT* (mils)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	Total (Gal/Sq)	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
20 Year	2.5	27	.75	.75	1.50	13	.40	.40	.80	4.5	4.80	44.5	Yes	Yes

* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor.
Note: DFT for 3-coursed rates includes 6 mils for the fabric.

+ Eligible for Kymax™ Roofing Coating 10-Year Limited Warranty (color) in addition to the enhanced system warranty or guarantee.