

UNISIL HS QUICK SPEC

CORRUGATED STRUCTURAL TRANSITE PANELS (UH-8)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at www.gaf.com.



METHOD REQUIREMENTS

Required:

- O Moisture survey required
- O Remove and replace any wet areas
- O Repair membrane with like materials
- O Roof must be clean, dry and tight
- O Apply at 40°F (4°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 8 hours
- Adhesion test required
- O Power washing required

Recommendations:

 Refer to Technical Data Sheet for product specific application and surface temperature restrictions.

Installation Overview:

- 1. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0 pounds per linear inch (PLI). Test patches should be applied with rates listed below.
- Power-wash substrate to remove contaminants that could negatively affect adhesion. Allow roof to completely dry.
- Tighten/replace existing fasteners. Encapsulate with appropriate flashing material.
- 4. Prime per chart below.
- 5. Treat all roof penetrations, drains, curbs, and scuppers. (Refer to Substrate Preparation section for requirements)
- Treat transite gaps in excess of 1/16" with compatible caulk prior to seam treatment. (Refer to Substrate Preparation Seam Treatment Guide for requirements)
- 7. Apply coating per the chart below:

CLEAN / PRIME					
	Product	Rate (Gal/Sq)			
Cleaner	Cleaning Concentrate (diluted)	0.5 - 0.7			
Primer	Multi-Purpose Primer	0.50 - 0.67			

SEAMS & DETAILS						
Treatment Type	Product		Total (linear ft/gal)+	DFT* (mils)		
3-Coursed Rates	Silicone Mastic and Fabric	2.50	75	45		
Flashing Grade Only Rates	Silicone Mastic	4.00	50	63		

Note: For other product options, please refer to our Seam Treatment Guide. ²Flashing rates are based on a 6" (152 mm) width.

CORRUGATED STRUCTURAL TRANSITE PANELS						
	Total		Warranties/Guarantees Available			
Coverage Term	Gal/Sq‡	DFT* (mils)	Emerald Pledge™	Diamond Pledge™		
10 Year	1.75	27	Yes	Yes		
15 Year	2.25	35	Yes	Yes		
20 Year	2.50	39	Yes	Yes		

^{*} Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor. Note: DFT for 3-coursed rates includes 6 mils for the fabric.

‡Coating may be applied in a single pass, as long as the substrate and slope conditions allow (no slumping), and the required DFT (mils) are met.

Important note Corrugated structural transite panels may contain asbestos. Follow all applicable local, state and federal regulations concerning asbestos. Under no circumstances does GAF have any liability for any damages, costs or expenses arising out of or associated with the pre-exsisting presence of asbestos containing materials or any other allgedly hazardous substances or materials on the roof to which the new GAF roofing materials are being applied.