

UNISIL QUICK SPEC

GRANULATED ASPHALTIC (UN-6)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at www.gaf.com.



METHOD REQUIREMENTS

Required:

- O Moisture survey required
- O Remove and replace any wet areas
- O Repair membrane with like materials
- O Roof must be clean, dry and tight
- O Apply at 40°F (4°C) and rising with no rain, dew, fog or freezing temperatures in forecast for 8 hours
- O Adhesion test required
- O Power washing required
- O New membranes should be aged at least 30 days; 90 days is ideal.

Restrictions:

Do not apply over gravel surfaced substrates.

Recommendations:

• Refer to Technical Data Sheet for product specific application and surface temperature restrictions.

Installation Overview:

- 1. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0 pounds per linear inch (PLI). Test patches should be applied with rates listed below.
- 2. Power-wash substrate to remove contaminants that could negatively affect adhesion. Allow roof to completely dry.
- 3. Prime per chart below.
- 4. All loose seams must be 3-coursed. All other seams must be treated with flashing grade only, no fabric required. (Refer to Substrate Preparation section for requirements)
- 5. Treat "alligatored" areas, surface cracks, roof penetrations, drains, curbs and scuppers. (Refer to Substrate Preparation section for requirements)
- 6. Apply coating per the chart below:

SURFACE PREP							
	Product	Rate (Gal/Sq)					
Cleaner	Cleaning Concentrate (diluted)	0.5 - 0.7					
Primer	Multi-Purpose Primer	1.0-1.3					

SEAMS & DETAILS									
Treatment Type	Product	Total (Gal/Sq)	Total (linear ft/ gal) ⁺	DFT* (mils)					
3-Coursed Rates	Silicone Mastic and Fabric	2.50	75	45					
Flashing Grade Only Rates	Silicone Mastic	4.00	50	60					

Note: For other product options, please refer to our Seam Treatment Guide. ²Flashing rates are based on a 6" (152 mm) width.

GRANULATED ASPHALTIC									
Coverage Term	Coating			Total		Warranties/Guarantees Available			
	1st Coat (Gal/Sq)	2nd Coat (Gal/Sq)	3rd Coat (Gal/Sq)	Gal/Sq	DFT* (mils)	Emerald Pledge™	Diamond Pledge™		
10 Year	1.50	1.00		2.50	28	Yes	Yes		
15 Year	1.25	1.00	1.00	3.25	37	Yes	Yes		
20 Year	1.50	1.50	1.00	4.00	46	Yes	Yes		

^{*} Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor.

Note: DFT for 3-coursed rates includes 6 mils for the fabric.